



## PRODUCT SPECIFICATIONS

|                      |                  |
|----------------------|------------------|
| Color                | Gray             |
| Resin                | PVC              |
| Specific Gravity     | 0.934±0.04       |
| Brookfield Viscosity | Minimum 1600 cps |
| VOC Content          | 361 g/L          |
| Shelf-life           | 3 Years          |

## 711 ECO™

Weld-On® 711 ECO™ is a code compliant cement with 30% lower solvent emission rate and significantly reduced odorous fumes than the current solvent cements in the market – resulting in an improved workplace environment for pipe installers.

The 711 ECO is a gray, ultra low VOC, heavy bodied, medium setting, maximum strength PVC solvent cement, with great gap filling properties, for all classes and schedules of PVC pipe and fittings, including Schedule 80, with interference fit through 12 inch (315 mm) diameter.

- Meets ASTM D2564 and CSA B137.3 & B181.2
- Meets 2023 SCAQMD Rule 1168/316A – low VOC regulations
- Credit can be earned per LEED® (Leadership in Energy and Environmental Design), IEQ Credit 4.1.
- Certified by NSF International to NSF/ANSI Standard 14 and 61 and the Uniform Plumbing Code for use on potable water applications.

EN 14814  
EN 14680



UK  
CA



**WARNING:** This product can expose you to chemicals including vinyl chloride, which are known to the State of California to cause cancer. For more information go to [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov).

### SPECIAL PRECAUTION

Weld-On solvent cements must never be used in plastic piping system using or being tested by compressed air or gases; including air-over-water booster. Do not use in conjunction with flue gas ventilation systems.

Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

This product is intended for use by skilled individuals at their own risk. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Detailed directions on making solvent cemented joints are printed on the container label. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.

**Refer to the current Safety Data Sheet for additional safety precautions, first-aid, storage, handling, transportation and disposal information.**

**Storage temperature: 40°F (5°C) – 110°F (43°C)**

**Refer to website for complete Terms and Conditions.**

